

Aluminum – Magnesium Powder 0-300µm

Application: Pyrotechnics, refractories

Composition: Al-Mg-alloy
Al 50,0 % (+/- 2 %)
Mg 50,0 % (+/- 2 %)
Fe max. 0,2 %
Cl max. 0,3 %
others max. 0,2 %

Grain size: Powder < 300 µm
Sieve analysis due to JEL 200
Sieve inlet: DIN ISO 3310-1

| | |
|----------|-----------|
| > 300 µm | max. 5 % |
| > 100 µm | 45 – 70 % |
| < 40 µm | max.15 % |

Density: 0,95 - 1,00 g / cm³

Special Properties: Passivated with oil or stearin

Packing: UN certified steel drums with 216 l

