

Fluidized Lime K 100

Application:	Desulfurization of hot metal Desulfurization of steel For monoinjection and coinjection with Magnesium
Composition:	CaO > 94 % L.O.I. max. 3 % Additives for increased efficiency. Fluidizing reagents.
Granulation:	> 0,09 mm max. 5 % > 0,125 mm 0 %
Bulk Density:	Approx. 900 kg/m ³
Special Properties:	Excellent flowability. A special coating guarantees the lime's flowability for a period of min. 3 months.
Packing:	silos, tanker, flow bins

