



Juli 2008  
revised in February 2018

## **KM 110 L (coarse) Injection Blend**

**Application:** Desulfurization of hot metal,  
.

**Composition:** 10 % Mg alloy  
90 % reactive, softburned lime with ultralow Sulfur content.

**Granulation:** Magnesium alloy:  
(DIN ISO 3310) > 1.0 mm 0 %  
(EN 12485) > 0.8 mm max 5 %  
0.5 - 0.8 mm 35 - 50 %  
0.2 - 0.5 mm 35 - 50 %  
< 0.2 mm traces

**Lime:** < 0.1 mm 100 %

**Bulk Density:** approx. 1.000 kg/m<sup>3</sup>  
(DIN ISO 697)

**Special Properties:** Good flowability due to special additives.  
The product can be adjusted to the specific requirements of the steel plant for optimal efficiency.

**Packaging:** Silotruck