

ALMAMET

January 2015

Magnesium Powder MGP 0 – 100µm

Application:	Pyrotechnics						
Composition:	Made from Mg min. 99,90 %						
Granulation:	Mg powder 0/100 µm Typical sieve analysis to JEL 200 sieve inlet: DIN 3310-1 <table><tr><td>> 100 µm</td><td>max.10%</td></tr><tr><td>> 63 µm</td><td>40-70 %</td></tr><tr><td>< 63 µm</td><td>min.30%</td></tr></table>	> 100 µm	max.10%	> 63 µm	40-70 %	< 63 µm	min.30%
> 100 µm	max.10%						
> 63 µm	40-70 %						
< 63 µm	min.30%						
Apparent Density:	0,55 – 0,65 kg / dm ³						
Special Properties:	Due to a special production procedure a low oxide content is achieved						
Packaging:	UN-CERTIFIED 210-L STEEL DRUMS						

