

Pellets 70/30

Application:	Metallurgical Slag conditioning for better desulfurization in Hot Metal and Steel Mills, Ladle Furnace Treatment in Secondary Metallurgy
Composition:	CaC ₂ 70% Al ₂ O ₃ 30 %
Bulk density:	approx. 2,0 kg*dm ⁻³
Appearance:	dark-grey pieces
Geometric size:	pillow shape 25 x 40 mm
Packing:	In steeldrums of different sizes, may also be packed in 10 kg PE-bags Container (IBC)

